


YUVARLAK BETONARME ÇELİK ÇUBUĞU (B.A. DEMİRİ)

STEEL MATERIAL

TS 708 - 1985 la

DIN 488 - 1972 Bst 22/34 GU



PROPERTIES FOR DESIGNING

TS 708 - 1985

DIN 488 - 1972

Standart Çaplar	Metretul Ağırlığı G (Kg/m)	Çubuk Alanı F (m ²)	Çubuk Hacmi W (m ³)	Çubuk Çevresi U (cm ² /m)	Standart Boy (m)
6	0.222	0.283	0.021	189	KANGAL
8	0.395	0.503	0.050	251	KANGAL
10	0.617	0.785	0.098	314	KANGAL
12	0.888	1.130	0.170	377	12.00 m
14	1.210	1.540	0.269	440	12.00 m
16	1.580	2.010	0.402	503	12.00 m
18	2.000	2.540	0.573	565	12.00 m
20	2.470	3.140	0.785	628	12.00 m
22	2.980	3.800	1.050	691	12.00 m
24	3.550	4.520	1.360	754	12.00 m
25	3.850	4.910	1.530	785	12.00 m
26	4.170	5.310	1.730	817	12.00 m
28	4.830	6.160	2.160	880	12.00 m
30	5.550	7.070	2.650	942	12.00 m
32	6.310	8.040	3.220	1010	12.00 m